

Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A catalyst for purifying an exhaust gas, comprising:
zirconia particles; and
a transition metal layer in which at least part of a transition metal is solved into said zirconia particles and which covers at least a part of a surface of said zirconia particles in a lamellar ~~manner~~manner;

wherein at least a part of said transition metal is solved into zirconia.

2. (Original) The catalyst according to claim 1, wherein said zirconia particles are heat-resistant zirconia particles.

3. (Original) The catalyst according to claim 2, wherein said transition metal layer is formed by loading a salt of a transition metal on said heat-resistant zirconia particles and thereafter calcining it at 800 °C or more in an inert gas atmosphere or an oxidizing gas atmosphere.

4. (Original) The catalyst according to claim 2, wherein at least one member selected from the group consisting of neodymium and cerium is added in an amount of from 1 to 80 atomic % with respect to zirconium in said heat-resistant zirconia particles, and at least a part of an oxide, being composed of at least one member selected from the group consisting of neodymium and cerium, forms a solid solution or a composite oxide with zirconia therein.

5. (Original) The catalyst according to claim 1, wherein said transition metal layer includes at least one metallic element selected from the group consisting of iron, nickel, cobalt and copper.

6. (Original) The catalyst according to claim 1 being further loaded with a noble metal.

7. (Original) The catalyst according to claim 1, wherein said transition metal layer covers the surface of said zirconia particles by a rate of from 10 to 80%.

8. (Original) The catalyst according to claims 1, wherein said transition metal layer is formed in an amount of from 2 to 10 parts by weight with respect to 100 parts by weight of said resistant zirconia particles.

9. (Original) The catalyst according to claim 6, wherein said noble metal is at least one member selected from the group consisting of platinum, palladium, rhodium, ruthenium and iridium.

10. (Original) The catalyst according to claim 6, wherein said noble metal is loaded in an amount of from 0.01 to 20 g with respect to 100 g of said catalyst.

11. (Currently Amended) A catalyst for purifying an exhaust gas, comprising:
a co-catalyst powder including zirconia particles, and a transition metal layer in which at least a part of a transition metal is solved into said zirconia particles and which covers at least a part of a surface of said zirconia particles in a lamellar manner; and
at least one member selected from the group consisting of a titania powder and a zeolite ~~powder-powder~~;

wherein at least a part of said transition metal is solved into zirconia.

12. (Original) The catalyst according to claim 11, wherein said zirconia particles are heat-resistant zirconia particles.

13. (Original) The catalyst according to claim 11, wherein said transition metal layer is formed by loading a salt of a transition metal on said heat-resistant zirconia particles and thereafter calcining it at 800 °C or more in an inert gas atmosphere or an oxidizing gas atmosphere.

14. (Original) The catalyst according to claim 12, wherein, in said heat-resistant zirconia particles, at least one member selected from the group consisting of neodymium and

cerium is added in an amount of from 1 to 80 atomic % with respect to zirconium, and at least a part of an oxide, being composed of at least one member selected from the group consisting of neodymium and cerium, forms a solid solution or a composite oxide with zirconia.

15. (Original) The catalyst according to claim 11, wherein said transition metal layer includes at least one metallic element selected from the group consisting of iron, nickel, cobalt and copper.

16. (Original) The catalyst according to claim 11 being further loaded with a noble metal.

17. (Original) The catalyst according to claim 11, wherein said titania powder exhibits a BET specific surface area of $50 \text{ m}^2/\text{g}$ or more.

18. (Original) The catalyst according to claim 11 comprising said titania powder in an amount of from 20 to 70% by weight with respect to the entire catalyst.

19. (Previously Presented) The catalyst according to claim 11, wherein said zeolite powder is composed of at least one member selected from the group consisting of mordenite, ZSM-5, USY, ferrierite and zeolite beta.

20. (Original) The catalyst according to claim 11 comprising said zeolite powder in an amount of from 10 to 30% by weight with respect to the entire catalyst.

21. (Original) The catalyst according to claim 12, wherein said transition metal layer covers the surface of the heat-resistant zirconia particles by a rate of from 10 to 80%.

22. (Original) The catalyst according to claim 12, wherein said transition metal layer is formed in an amount of from 2 to 10 parts by weight with respect to 100 parts by weight of the heat-resistant zirconia particles.

23. (Original) The catalyst according to claim 11 comprising said co-catalyst powder in an amount of from 50 to 80% by weight with respect to the entire catalyst.

24. (Original) The catalyst according to claim 16, wherein said noble metal is at least one member selected from the group consisting of platinum, palladium, rhodium, ruthenium and iridium.

25. (Original) The catalyst according to claim 16, wherein said noble metal is loaded in an amount of from 0.01 to 20 g with respect to 100 g of the catalyst.